# **ALUMINIUM**

# 6063 - T6



#### 6063 - T6

Aluminium 6063-T6 is a medium-strength alloy in the Al-Mg-Si series, known for its excellent extrudability, moderate strength, good weldability and corrosion resistance. It's widely used for extruded architectural profiles and decorative finishes. The T6 temper indicates that the metal has been solution heat-treated and artificially aged to achieve a specific level of mechanical properties.

## **KEY FEATURES**

- Excellent weldability using conventional ways
- Good machinability
- Easily formed and extruded
- Good corrosion resistance
- Suitable for complex shapes and profiles

CHEM	ICAL P	ROPER	TIES						
Magnesium	Silicone	Iron (Fo)	Manganese	Zinc	Copper	Titanium	Chromium	Other	Aluminium
(Mg)	(Si)	(Fe)	(Mn)	(Zn)	(Cu)	(Ti)	(Cr)	Elements	(AI)
0.45-0.9%	0.2-0.6%	0.35%	0.1%	0.1%	0.1%	0.1%	0.1%	0.05%	rest

MECHANICAL PROPERT	IES
Tensile strength (N/mm²)	180
Yield strength (N/mm²)	110
Elongation (% at break)	8
Proof stress (MPa)	50
Hardness - Brinell (HB) max	60

PHYSICAL PROPERTIES						
Density (kg/m³)	270					
Modulus of elasticity (Gp	69					
M	0-100°C (µm/m/°C)	23.6				
Mean coefficient of	0-350°C (µm/m/°C)	24.6				
thermal expansion	0-538°C (µm/m/°C)	25.3				
Thermal	at 100°C (W/m.K)	210				
conductivity	at 500°C (W/m.K)	250				
Specific Heat 0-100°C (J	92					
Electrical conductivity (I/	55					
Melting point (°C)	600					

## **MARKET SECTORS**





Automotive Industry

Beams, columns, scaffolding, window frames, door frames

Automotive trim, roof rails, structural components





Electrical Industry

Hulls, masts, superstructures, boat components

Electrical enclosures, housings, heat sinks





Aerospace Industry

Extrusions, profiles, jigs, fixtures, tooling

Interior panels, seat frames, components, military vehicles



Tel: +44 (0)1204 368600 Email: sales@steel-dynamics.co.uk Visit our website: www.steel-dynamics.co.uk