

NICKEL ALLOY

201 - 2.4068



201- 2.4068

Nickel Alloy 201 is a commercially pure wrought nickel alloy, similar to Nickel Alloy 200 but with a lower carbon content. This reduction in carbon content helps to prevent embrittlement at elevated temperatures due to the formation of graphite. Like Nickel Alloy 200, Alloy 201 is primarily composed of nickel, with very low levels of other impurities. It is valued for its purity, corrosion resistance and thermal and electrical conductivity properties.

KEY FEATURES

- High thermal and electrical conductivity
- Excellent corrosion resistance
- Low gas content
- Good mechanical properties
- Ease of fabrication

CHEMICAL PROPERTIES

Nickel (Ni)	Iron (Fe)	Silicone (Si)	Manganese (Mn)	Copper (Cu)	Carbon (C)	Sulphur (S)
99%	0.4%	0.35%	0.35%	0.25%	0.15%	0.01%

MECHANICAL PROPERTIES

Tensile strength (N/mm ²)	380-550
Yield strength (N/mm ²)	105-310
Elongation (% in 4D)	40-55
Hardness - Rockwell (HRB) max	45-65
Hardness - Brinell (HB) max	105-170

PHYSICAL PROPERTIES

Density (kg/m ³)	8890	
Modulus of elasticity (Gpa)	204	
Mean coefficient of thermal expansion	0-100°C (µm/m/°C)	13.3
	0-350°C (µm/m/°C)	14.0
	0-538°C (µm/m/°C)	14.8
Thermal conductivity	at 100°C (W/m.K)	60.0
	at 500°C (W/m.K)	39.0
Specific Heat 0-100°C (J/kg.K)	444	
Electrical resistivity (nΩ.m)	90	
Melting point (°C)	1445	

MARKET SECTORS



Electrical Industry

Contacts, connectors, anodes, cathodes, heating elements



Chemical Processing

Reactors, vessels, heat exchangers, valves, piping



Oil & Gas Industry

Downhole equipment, valves, fittings, pipelines



Marine Equipment

Shipbuilding, seawater piping systems, propeller shafts, pumps



Food & Beverage Industry

Cookware, brewing vats, food processing machinery



Aerospace Industry

Aircraft components, aerospace structures, gas turbines