

# NICKEL ALLOY

## K500 - 2.4375



### K500 - 2.4375

Nickel Alloy K500, also known as 2.4375 or Monel K500, is a nickel-copper alloy that can be age-hardened by adding aluminum and titanium. It is known for its resistance to corrosion and its ability to maintain good mechanical properties in challenging environments, especially in marine and chemical environments, and high strength at elevated temperatures.

### KEY FEATURES

- Excellent corrosion resistance
- High strength
- Non-magnetic
- Good ductility and toughness
- Low magnetic permeability

### CHEMICAL PROPERTIES

Nickel (Ni)	Copper (Cu)	Aluminium (Al)	Iron (Fe)	Manganese (Mn)	Silicone (Si)	Titanium (Ti)	Carbon (C)	Sulphur (S)
<b>63%</b>	<b>27-33%</b>	<b>2.3-3.2%</b>	<b>2%</b>	<b>1.5%</b>	<b>0.5%</b>	<b>0.35-0.85%</b>	<b>0.25%</b>	<b>0.1%</b>

### MECHANICAL PROPERTIES

Tensile strength (N/mm <sup>2</sup> )	<b>1100</b>
Yield strength (N/mm <sup>2</sup> )	<b>790</b>
Elongation (% in 4D)	<b>20</b>
Hardness - Rockwell (HRB) max	<b>75-85</b>
Hardness - Brinell (HB) max	<b>315</b>

### PHYSICAL PROPERTIES

Density (kg/m <sup>3</sup> )	<b>8440</b>	
Modulus of elasticity (Gpa)	<b>179</b>	
Mean coefficient of thermal expansion	0-100°C (µm/m/°C)	<b>13.4</b>
	0-350°C (µm/m/°C)	<b>13.9</b>
	0-538°C (µm/m/°C)	<b>14.5</b>
Thermal conductivity	at 100°C (W/m.K)	<b>17.2</b>
	at 500°C (W/m.K)	<b>20.1</b>
Specific Heat 0-100°C (J/kg.K)	<b>418</b>	
Electrical resistivity (nΩ.m)	<b>242</b>	
Melting point (°C)	<b>1350</b>	

### MARKET SECTORS



**Oil & Gas Industry**

Downhole equipment, pump shafts, valve stems, tubing



**Chemical Processing**

Reactors, vessels, heat exchangers, piping systems



**Marine Equipment**

Marine shafts, valves, fasteners, pump and valve components



**Electrical Industry**

Electrical connectors, springs, switchgear components



**Aerospace Industry**

Fasteners, springs, parts, missile systems, fuel tanks



**Power Generation**

Turbine components, blades, boiler feedwater systems



**Steel Dynamics UK**

Tel: +44 (0)1204 368600  
Email: [sales@steel-dynamics.co.uk](mailto:sales@steel-dynamics.co.uk)

Visit our website:  
[www.steel-dynamics.co.uk](http://www.steel-dynamics.co.uk)